



cosmetics & care **waxes**

paracera[®]

waxes for **cosmetic and
pharmaceutical** preparations

Experience performance in the
way our **wax additives safely
deliver** the desired effect

○ waxes adhesives coatings

 **paramelt**
experience. performance.

Our Paracera® products are a range of high purity mineral, natural and specialty narrow-cut waxes widely used for personal care and decorative cosmetics. Paracera® products offer leading brand owners high quality and consistent performance.

	Product	Color	Drop melting point (°C) ASTM D 3954	Congeeing point (°C) ASTM D 938	Penetration at 25°C (0.1mm) ASTM D 1321	Creams and ointments	Decorative cosmetics	Stick form products	Description
Paraffin waxes	Paracera P	White	n/a	58-62	13-17	•	•	•	Used in ointments and cream formulations to improve consistency. Adds gloss and moisture retention to sticks and color cosmetics. Its good oil absorption permits the addition of high proportions of effective substances to the fat phase.
Ozokerite waxes*	Paracera M	White / Off white	72-80	68-72	14-18	•	•	•	The most versatile wax in our range. Formulated with a well-balanced proportion of straight and branched chain hydrocarbon waxes. The product has consistency regulating and gel forming properties. Due to good absorption of mineral and vegetable oils, stable and fine crystals are formed.
	Paracera W 80	White / Off white	82-88	75-80	9-13	•	•	•	A balanced formulation of mineral hydrocarbon waxes that delivers dry consistency when used in creams and provides excellent oil binding properties for stick forms. Used as a regulator in preparations for decorative cosmetics when a hard and high melting point wax is required.
	Paracera 11946	White	88-96	79-85	5-9	•	•	•	A blend of primarily linear mineral and synthetic waxes that imparts advantageous properties in warmer climates due to its higher temperature stability. It has superior gel forming properties with oils and excellent gloss from enhanced macro crystal formation. Also used to give stick products good structure and hardness and prevent tackiness in decorative cosmetics.
	Paracera 13863	Max. Yellowish	96-106	86-94	4-10	•	•	•	A formulated mixture of hydrocarbon waxes creating an Ozokerite structure and performance with increased temperature stability. The Ozokerite type composition allows for both good oil gelling and enhanced oil binding properties. For use in sticks, decorative cosmetics and skin care, it stabilizes the final product, enhances hardness and temperature resistance and modifies rheology.
Microcrystalline waxes	Paracera L	Yellowish / Light yellow	approx. 65	57-63	20-30	•	•	•	A hydrocarbon wax, of microcrystalline structure, that distinguishes itself by its unique low congealing point. The low oil content and flexible character makes it very suitable for many cosmetic applications where good oil binding or viscosity regulation is required.
	Paracera MW	Off white / Ivory	78-86	73-79	22-32	•	•	•	A mixture of hydrocarbon waxes composed of predominantly branched chains, provides this microcrystalline wax with consistency, regulating and gel forming properties. Forms fine crystals and stable structures due to its good absorption of mineral and vegetable oils.
	Paracera H	Off white / Ivory	approx. 88	80-86	8-16	•	•	•	A hydrocarbon wax, of microcrystalline structure, that is distinguished by its high congealing and melting points. Used as a regulator in preparations for decorative cosmetics and its superior oil binding behavior makes it very suitable for stick forms.
Narrow cut waxes	Paracera N 101	Max. Off white	98-104	93-97	0-5	•	•	•	It is a narrow molecular weight distribution of primarily linear hydrocarbons, with highly efficient material property modifications at low additive levels. Has excellent oil gelling properties and imparts increased temperature stability and hardness, gloss and structure in stick products and to modify viscosity of oil components.
	Paracera N 106	Max. Off white	103-109	98-102	0-5	•	•	•	It is a narrow molecular weight distribution of primarily linear hydrocarbons, with highly efficient material property modifications at low additive levels. Has excellent oil gelling properties and imparts increased temperature stability and hardness, gloss and structure in stick products and to modify viscosity of oil components.
Specialty waxes	Paracera C 44	Light yellow	79-85	n/a	0-8	•	•	•	A blend of Carnauba and other waxes that increases hardness and gloss of decorative cosmetics and sticks. It gives increased temperature stability to cosmetic products and is a good oil binder and co-emulsifier.
	Beeswax Blend 164	Off white	61-65	61-65	n/a	•	•	•	A blend of beeswax with other ingredients. In this partially synthetic beeswax the chemical, physical and performance characteristics are comparable with pure beeswax.
	Beeswax Blend 166	Yellow	61-65	61-65	n/a	•	•	•	A blend of beeswax with other ingredients. In this partially synthetic beeswax the chemical, physical and performance characteristics are comparable with pure beeswax.
Beeswaxes	Beeswax Care 144	Ivory	61-66	61-65	n/a	•	•	•	100% pure bleached beeswax. A natural emulsifier, it stabilizes creams and lotions, increases compatibility of materials in decorative cosmetics and works as an emollient and oil binder in stick products.
	Beeswax Care 146	Yellow	61-66	61-65	n/a	•	•	•	100% pure refined beeswax. A natural emulsifier, it stabilizes creams and lotions, increases compatibility of materials in decorative cosmetics and works as an emollient and oil binder in stick products.

* For cosmetic and pharma applications, formulated blends of petroleum waxes have replaced the naturally occurring mineral wax ozokerite, as original ozokerite is no longer commercially available. The original ozokerite wax was obtained from bituminous coal. The chemistry was a blend of linear hydrocarbons (paraffin) and branched hydrocarbons (microcrystalline wax), but it had darker color and odors due to contaminants. The formulated ozokerite products are chemical equivalents to the natural occurring material but are more highly purified from contaminants. INCI reporting requirements differ regionally around the world. As the Paracera line of products is produced in the European Union, we comply with the European Commission Database Cosing for our INCI designations. Cosing requires INCI names that most accurately reflect the material description, which for waxes is frequently more highly dependent on the processing of materials than the composition itself. The materials in this group are compositionally ozokerite, but our INCI designations will reflect the closest Cosing designation based on the processing.



This overview is a **limited selection** of our product range. For regulatory information please **contact your local Paramelt representative.**



We are **Paramelt**

Founded in 1898, Paramelt has over 120 years of experience and today is a global producer of wax blends, adhesives and specialty dispersions. Operating from production sites in The Netherlands, United Kingdom, the USA and China we work together in a team of about 500 employees around the world. In most of our core applications Paramelt is the acknowledged market leader.

Paracera® is a registered trademark of Paramelt Information and details given in this document, particularly any recommendations for application and use of our products are based on careful laboratory tests and prevailing practical experience and are believed to be correct at time of publication. For more information: paramelt.com/disclaimer

Paramelt Europe

Costerstraat 18
1704 RJ Heerhugowaard
The Netherlands
t +31 72 57 50 600

Paramelt USA

2817 McCracken Street,
Muskegon, MI 49441
United States of America
t +1 231 759 7304

Paramelt Asia

109 Sutong Road,
Suzhou Industrial Park
Suzhou, Jiangsu 215021, China
t +86 512 6761 6618

○ waxes adhesives coatings

www.paramelt.com


paramelt
experience. performance.